

6111 Shakespeare Rd.
 Columbia, SC 29223
 Tel. (803) 754-7011
 Fax. (803) 754-7991

www.shakespearemonofilaments.com

M-7 WonderThread

WonderThread®						
	Average Diameter	Average Denier	Approx. Yds./Lb.	Typical Tensile Lbs.	Average Elongation @1.75 G/D	Average Shrinkage* @ 350 F, 10 min
	.003"	60	75,000	.6	25%	4.5%
	.004"	100	44,600	1.0	25%	4.5%
	.005"	160	28,000	1.6	25%	4.5%
	.006"	225	19,800	2.3	25%	4.5%
	.007"	310	14,400	3.1	25%	4.5%



*WonderThread & Whispertouch are registered trademarks of Shakespeare Monofilament Division