


- Nylon 6,6
- Medium Shrinkage
- Moderate Modulus


TYPICAL PROPERTIES

DIAMETER	SHRINKAGE	EXT. @ 1.75GPD
0.13mm	12.0% @177°C	3.5%

Stress Strain



Contractive Force
0.01 GPD Pretension



Shrinkage
Hot Air Oven

