


- Nylon 6
- High Shrinkage
- Moderate Modulus
- High Shrinkage Force


TYPICAL PROPERTIES

DIAMETER	SHRINKAGE	EXT. @ 1.75GPD
0.20mm	18.0% @175°C	7%
0.40mm	15.0% @175°C	7%

Stress Strain



Contractive Force 0.01 GPD Pretension



Shrinkage Hot Air Oven

