


- Standard Molecular Weight
- Polyester
- Low Shrinkage
- Low Modulus
- Welt Yarn


TYPICAL PROPERTIES

DIAMETER	SHRINKAGE	EXT. @ 3GPD
0.20mm	3.0% @200°C	22%
0.40mm	3.0% @200°C	24%

Stress Strain



Contractive Force
0.01 GPD Pretension



Shrinkage
Hot Air Oven

